

<u> I Travertini</u>

SPECIFICATION

Material

Porcelain stoneware. Classified in GROUP BIa UGL con $E_V \le 0.5\%$. Complies with all the requirements of UNI EN 14411 ISO 13006 APP. G standards.



COLOR	SIZES & SURFACES	THICKNESS
Bianco Vein Cut V2		
Bianco Cross Cut V2	Mega Matte Rectified (6 mm) 120x280	
Beige Vein Cut V2	REALUP/STRIDEUP Matte Rectified (9 mm) 120x120 . 80x160 . 60x120 . 60x60 . 30x60	6 mm
Beige Cross Cut V2	Antislip Rectified (9 mm) 60x120	9 mm
Grigio Vein Cut V2	<u>Ribbed (9 mm)</u> 60x120	20 mm
Grigio Cross Cut V2	Open Antislip Rectified (20 mm) 60x120	
Rosso Vein Cut V3		

Process certified according to the ISO 9001 quality standard

Product obtained from exceptionally pure, choice quality raw materials, including light-coloured clays, feldspar fluxes, kaolins, sands and coloured ceramic pigments. Pressing in hydraulic presses allows a pressure of over 500kg/cm2 to be applied to the product, guaranteeing dimensional precision, planarity and high mechanical strength. The product's colours and patterns are achieved with the innovative Digital Technology. The materials are fired in single-layer roller kilns at temperatures of over 1,220°C.

Green building certified environmental sustainability

The tiles in the I Travertini collection are ideal for eco-sustainable building:

- They are produced in plants which have an EMAS-ISO 14001 certified environmental management system.
- They help to obtain credits for the construction of buildings in accordance with the LEED certification programme.

Size	
Finishes	
<u>Color</u>	Type



























I Travertini

SPECIFICATION

















TECHNICAL TABLE PORCELAIN STONEWARE

CONFORMING TO STANDARDS

EN 14411 ISO 13006 ANNEX G GROUP Bla UGL CON Ev $\leq 0.5\%$

	PHYSICAL PROPERTIES	TESTING METHOD	REFERENCE STANDARD			PRODUCT VALUES
		EN ISO 10545-2		7cm ≤ N < 15 cm (mm)	N ≥ 15 cm (%) (mm)	Rectified
	Sizes		Length and width	±0.9	±0.6 ±2.0	±0.2 %
			Thickness	±0.5	±5.0 ±0.5	±5 %
			Linearity	±0.75	±0.5 ±1.5	±0.2 %
			Wedging	±0.75	±0.5 ±2.0	±0.2 %
			Warpage	±0.75	±0.5 ±2.0	±0.2 %
			Appearance: percentage of acceptable tiles, per lot	95 % min.	95 % min.	
•	Water absorption %	EN ISO 10545-3	Ev ≤ 0,5%			< 0,1%
1	Modulus of rupture	ENUCO 10545 4	Valore medio 35 N/mm² min.			45 N/mm²
	Breakage resistence	EN ISO 10545-4	sp. > = 7,5 mm: min 1300 N sp. < 7,5 mm: min 700 N			2300 N (9 mm) 12500 N (20 mm)
0	Scratch resistance	EN ISO 10545-6	175 mm3 max.			Average < 150 mm3
←	Thermal expansion coefficient	EN ISO 10545-8	Declared value			6,8 MK ⁻¹
	Thermal shock resistance	EN ISO 10545-9	Pass according to iso 10545-1			* Resistant
攀	Frost resistance	EN ISO 10545-12	Pass according to iso 10545-1			* Resistant
	Resistance to low concentrations of acids and alkali		Declared value			* Resistant
	Resistance to high concentrations of acids and alkali	EN ISO 10545-13	Declared value			* Resistant
	Resistance to domestic chemicals and additives for swimming pools		UB min.			UA
*	Stain resistance of unglazed matte porcelain	EN ISO 10545-14	Declared value			* Resistant
8	Friction coefficient (slipperiness)	EN 16165 -	Annex A			Declared value
			Annex B			Declared value
		B.C.R.A D.M.236/ 89	If needed			> 0,40 Dry / > 0,40 Wet
		ANSI A326.3	If needed			≥ 0,42 Wet